

# HASTELLOY® W alloy

## Principal Features

HASTELLOY® W alloy (UNS N10004) is a solid-solution-strengthened super alloy that was developed primarily as a filler metal for welding of dissimilar alloys. It displays excellent dissimilar welding characteristics, and is widely used for that purpose in the gas turbine and aerospace industries. The properties of dissimilar weld joints made with alloy W are dependents upon the alloys joined, but are generally acceptable for a wide variety of combinations. Alloy W is also used as a wrought alloy for a limited number of ring-type applications in older gas turbine engines. HAYNES® 242® alloy is a more modern alloy, and should be considered as a substitute for alloy W in these ring applications (ask for publication H-3079).

## Nominal Composition

### Weight %

<b>Nickel:</b>	63 Balance
<b>Cobalt:</b>	2.5 max.
<b>Iron:</b>	6
<b>Chromium:</b>	5
<b>Molybdenum:</b>	24
<b>Tungsten:</b>	1 max.
<b>Manganese:</b>	1 max.
<b>Silicon:</b>	1 max.
<b>Vanadium:</b>	0.6 max.
<b>Carbon:</b>	0.12 max.

## Stress-Rupture Strength

### Bar (AMS 5755)

Test Temperature		Approximate Initial Stress to Produce Rupture in:					
		10 h		100 h		1000 h	
°F	°C	ksi	MPa	ksi	MPa	ksi	MPa
1300	705	-	-	34.5	240	27.5	190
1400	760	33	230	26	180	19	130
1500	815	24.8	170	18	125	12.4	85
1600	870	17.4	120	12	83	8	55
1700	925	11.7	81	7.9	54	5.2	36
1800	980	7.9	54	5.2	36	3.2	22

## Guided Bend Test Results

### 1/2 inch (12.7) Plate Weldments (GTAW) Using Alloy W Filler

Base Materials	Bend Radius	Results
188/ MULTIMET®	2t	No Cracks
625/ 718	2t	No Cracks
304 SS/ Carbon Steel	2t	No Cracks

# Heat Treatment, Weld Deposits (A) and Wrought Bar (B)

## Weld Deposits (A), Wrought Bar (B)

(A) None (B) 2165°F (1185°C)/15 minutes/WQ

## Physical Properties

Physical Property	British Units		Metric Units	
Density	RT	0.325 lb/in <sup>3</sup>	RT	9.00 g/cm <sup>3</sup>
Melting Temperature	2350-2510°F		1290-1375°C	
Mean Coefficient of Thermal Expansion	70-800°F	7.3 μin/in -°F	20-500°C	13.2 x 10 <sup>-6</sup> m/m·°C
	70-1000°F	7.4 μin/in -°F	20-600°C	13.2 x 10 <sup>-6</sup> m/m·°C
	70-1200°F	7.4 μin/in -°F	20-700°C	13.5 x 10 <sup>-6</sup> m/m·°C
	70-1400°F	7.8 μin/in -°F	20-800°C	14.2 x 10 <sup>-6</sup> m/m·°C
	70-1600°F	8.2 μin/in -°F	20-900°C	14.8 x 10 <sup>-6</sup> m/m·°C
	70-1800°F	8.4 μin/in -°F	20-1000°C	115.3 x 10 <sup>-6</sup> m/m·°C

RT= Room Temperature

## Tensile Properties

### Bar (AMS 5755)

Test Temperature		0.2% Offset Yield Strength		Ultimate Tensile Strength		Elongation
°F	°C	ksi	MPa	ksi	MPa	%
RT	RT	75.5	520	139.8	965	51
1000	538	54	370	120.8	835	52.5
1200	649	52.9	365	103.5	715	27
1400	760	55.5	385	88.5	610	20.3
1600	871	48.8	335	60.5	415	31.8
1800	982	23.6	165	32.4	225	47.5
2000	1093	10.6	73	17.4	120	79

RT=Room Temperature

### Typical All-Weld Metal Tensile Properties - Gas Tungsten

Condition	Test Temperature		0.2% Offset Yield Strength		Ultimate Tensile Strength		Elongation	Reduction of Area
	°F	°C	ksi	MPa	ksi	MPa	%	%
As-Welded	RT	RT	80	550	120	830	35	27
	1600	871	40	275	43	295	45	53
	RT	RT	115	795	160	1105	14	16
Aged 1000 h 1200°F (650°C)	-	-	-	-	-	-	-	-
	1400	760	64	440	84	580	27	38
Aged 1000 h 1400°F (760°C)	-	-	-	-	-	-	-	-
	-	-	-	-	-	-	-	-

# Tensile Properties Continued

## Gas Metal

Condition	Test Temperature		0.2% Offset Yield Strength		Ultimate Tensile Strength		Elongation	Reduction of Area
	°F	°C	ksi	MPa	ksi	MPa		
As-Welded	RT	RT	80	550	127	875	38	32
	1600	871	42	290	45	310	41	42
Aged 1000 h 1200°F (650°C)	RT	RT	110	760	153	1055	15	16
	-	-	-	-	-	-	-	-
Aged 1000 h 1400°F (760°C)	1400	760	58	400	82	565	30	47
	-	-	-	-	-	-	-	-

## Shielded Metal

Condition	Test Temperature		0.2% Offset Yield Strength		Ultimate Tensile Strength		Elongation	Reduction of Area
	°F	°C	ksi	MPa	ksi	MPa		
As-Welded	RT	RT	76	525	110	760	25	22
	1600	871	36	250	38	260	14	15
Aged 1000 h 1200°F (650°C)	RT	RT	108	745	128	885	8	8
	-	-	-	-	-	-	-	-
Aged 1000 h 1400°F (760°C)	1400	760	57	395	77	530	11	14
	-	-	-	-	-	-	-	-

# Tensile Properties Continued

## Transverse Tensile Properties for 1/2 in (12.7mm) Plate Weldments (GTAW) Using Alloy W Filler\*

Base Materials	Test Temperature		0.2% Offset Yield Strength		Ultimate Tensile Strength		Elongation	Reduction of Area
	°F	°C	ksi	MPa	ksi	MPa		
-								
X	RT	RT	58	395	113	780	52	55
	1600	871	33	230	42	290	39	65
188	RT	RT	73	505	128	885	201	301
	1600	871	51	350	58	400	361	601
MULTIMET®	RT	RT	62	425	116	800	49	65
	1600	871	32	215	42	290	28	42
625	RT	20	69	475	119	820	63	63
	1600	871	35	240	44	305	58	91
718	RT	RT	68	470	125	860	231	311
	-	-	-	-	-	-	-	-
304 SS	RT	RT	48	330	90	620	62	69
	-	-	-	-	-	-	-	-
Carbon Steel	RT	RT	60	415	72	495	14	50
	-	-	-	-	-	-	-	-
188/ MULTIMET®	RT	RT	66	455	117	805	35	64
	1600	871	34	235	47	325	19	19
625/ Alloy	RT	RT	62	430	131	905	432	422
	1600	871	39	270	48	330	51	95
304 SS/ Carbon Steel	RT	RT	51	355	71	490	17	51
	-	-	-	-	-	-	-	-

\*Failures in base metal unless otherwise indicated

<sup>1</sup>Failures in weld

<sup>2</sup>Failures in weld and base metal

All values are averages of 2-4 tests

# Specifications

## Specifications

<b>Bar Wire</b>	AMS 5786	AWS A5.14 & ASME SFA 5.14 (ERNiMo-3)
<b>Coated Electrodes</b>	AMS 578	AWS A5.11 & ASME SFA 5.11 (ENiMo-3)
<b>Bar, Rings and Forgings</b>	AMS 5755	-

### Disclaimer:

Haynes International makes all reasonable efforts to ensure the accuracy and correctness of the data in this document but makes no representations or warranties as to the data's accuracy, correctness or reliability. All data are for general information only and not for providing design advice. Alloy properties disclosed here are based on work conducted principally by Haynes International, Inc. and occasionally supplemented by information from the open literature and, as such, are indicative only of the results of such tests and should not be considered guaranteed maximums or minimums. It is the responsibility of the user to test specific alloys under actual service conditions to determine their suitability for a particular purpose.

For specific concentrations of elements present in a particular product and a discussion of the potential health effects thereof, refer to the Safety Data Sheets supplied by Haynes International, Inc. All trademarks are owned by Haynes International, Inc., unless otherwise indicated.